



Use of TiO₂ in Photocatalysis for Air Purification and Wastewater Treatment: A Review

Seba S. Mohammed*, Zainab Y. Shnain^{ID}, Mohammad F. Abid^{ID}

Chemical Engineering Dept., University of Technology-Iraq, Alsina'a street, 10066 Baghdad, Iraq.

*Corresponding author Email: che.19.13@grad.uotechnology.edu.iq

HIGHLIGHTS

- The advantages of TiO₂ -based as photocatalyst are reviewed in this study.
- The development of the group gap in photocatalyst (TiO₂) by different doping was investigated.
- Modification in the structure across the photocatalytic activity of TiO₂ is reviewed.
- Different preparation methods and applications of the Methodology of photocatalysts were also reviewed.

ARTICLE INFO

Handling editor: Mustafa H. Al-Furaiji

Keywords:

Heterogeneous photocatalyst; pollution degradation; photocatalytic nano semiconductors; modified titanium dioxide solar radiation.

ABSTRACT

This study reviews recent research on the synthesis and application of titanium dioxide (TiO₂)-based photocatalysts for environmental applications. The principles of non-homogenous photo-catalysis include utilizing a solid semiconductor, such as titanium dioxide Nano or macro, to form a stable suspension (heterogeneous phase) at the impact of irradiation to elevate a reaction at the surface interface of the different phases in the system. Recently, titanium dioxide has been considered the better semiconductor in non-homogenous photoinduced treatment. TiO₂-based photocatalysts have broad applications for industrial processes because of their exceptional physicochemical properties. Nevertheless, having a narrow band near the ultraviolet region limits its applications within visible radiation. As a result of this, there have been considerable research efforts to improve the visible light tendency of TiO₂ through modifications of its optical and electronic properties. Several strategies, such as coupling TiO₂ tightly and incorporating other metallic components during synthesis, have increased the bandgap of TiO₂ for visible light applications. Moreover, an overview of nanotechnology that could enhance the properties of TiO₂-based catalysts in an environmentally friendly way to decompose pollutants is also presented. The various TiO₂-based photocatalysts have wide applications in degrading recalcitrant pollutants in the air, water, and wastewater treatment under visible light.

1. Introduction

The past decades' successes in research and innovations have resulted in astronomical growth in industrial activities to meet the ever-increasing human demands. These anthropogenic activities from the various industries have adversely affected air and water quality through the discharge of industrial wastes, produce wastewater from oil refineries, and emissions of gaseous pollutants [1-3]. Of all the various types of pollution, using petroleum fuel for mobility has resulted in a severe emission of toxic gaseous pollutants and particulate matters into the environment, adversely affecting human health [4-6]. The most significant impact of these pollutions is often experienced among the populace living in the urban area or cities [7]. The high concentration of these pollutants in the environment, which has resulted in various chronic diseases, has been a significant concern for environmentalists and researchers [3, 8]. For instance, studies have shown that high human exposure to nitrogen oxide (NO_x) often results in asthma [9]. Hence, it is expedient to strategically reduce vehicular emissions, which will invariably lead to NO_x reduction and minimize its effect on human health [10]. Several methods have been explored and reported in the literature to mitigate the effects of NO_x from vehicular emissions on the environment.

One of the emerging techniques for mitigating gaseous pollutants is using heterogeneous photo-oxidation (HPO) [11- 12]. The HPO techniques entail using photocatalysts, mostly semiconductors, to degrade these recalcitrant organic pollutants in the presence of an active radiation source and an oxidizing agent. The radiation source could be solar ultraviolet or simulated light [13]. Enormous light irradiation is usually produced from the sun, estimated to be 0.2-0.3 moles of photons per hour in the range of 300-400 nm with a UV flux of 20-30 W/m² [14]. Hence, from the economic and environmental point of view, the sun has a great potential to be used as an irradiation source for photocatalytic degradation of organic pollutants [15]. Furthermore, the HPO techniques have been reported to have a promising route for mitigating the impact of NO_x and other gaseous substances released into the environment [16].




Figure 1: Application and Proportions of TiO₂ used in various sectors (Data for 2013, Merchant Research and Consulting, 2015 [22])

The oxidant used during the NO_x process is often based on very powerful oxidants, often referred to as hydroxyl radicals, that are usually generated during the photocatalytic process [17]. The hydroxyl radicals can oxidize a wide range of organic pollutants by converting them to harmless inorganic products [18]. Therefore, the HPO process has stimulated the interest in developing an effective electro-catalytic process that can be applied for air purification and treatment of wastes containing recalcitrant organic pollutants. These innovations have also resulted in introducing smart products into the markets that can be deployed to combat environmental pollutants in the past three decades [19].

Semiconductor-based photocatalysts such as titanium dioxide (TiO₂), tungsten trioxide (WO₃), and zinc oxide (ZnO) have been widely used for various applications in buildings, paving roads, vehicles side mirrors, lamps, and textiles [20- 21]. Specifically, TiO₂ has been widely applied for various industrial applications, as represented in Figure 1. For example, TiO₂ has been applied in ink pigment production, plastic paper, synthetic fiber, rubber, electric ceramics, paints, glass, and catalysts. In addition, a large proportion of the TiO₂ is applied in paint manufacturing. The annual global consumption of TiO₂ is increasing due to these numerous applications.

2. An Overview of Photocatalytic Semiconductors

The increasing interest in removing recalcitrant pollutants from polluted wastewater has led to the development of various inexpensive absorbents that can be easily applied [42]. Also, absorbents have been developed from alternative sources to make them accessible [44]. However, advancement in wastewater treatment has resulted in development of semiconductor materials that are very effective in cleaning up hazardous waste sites, pollution treatment, desalination, and environmental pollution awareness and control [45- 46]. Semiconductors, mostly metal oxides in nanostructures, have been employed in photocatalytic applications due to their excellent physicochemical properties such as band-gap, desired band edge position, large surface area, perfect morphology, and chemical stability, and reusability capability [24]. Table 1 shows that various semi-conductor-based metal oxide is similar in photocatalytic properties and capable of photoactivity under visible light, ultraviolet (UV) light, or a combination of visible and UV light irradiation with a band gap. TiO₂ and ZnO have been used as excellent photocatalysts to degrade numerous environmental contaminants. The increasing interest in TiO₂ and ZnO is due to their high photosensitivity, stability, and large band gap.

2.1 General Types and Characteristics of Titanium Dioxide

TiO₂ is abundant in nature as the fourth most easily found material and exists in three phases, namely anatase, rutile, and brookite [48]. The most stable crystalline phase-out of the three is anatase. Rutile, on the other hand, is commonly available, whereas brookite is very rare and often has scanty application. The properties of TiO₂ and ZnO are summarized in Table 2.

Amongst the various semiconductors, TiO₂ has the most comprehensive applications as a photocatalyst [23]. ZnO, which could be a viable alternative to TiO₂, has received less attention. Because of the large bandgap of ZnO compared to TiO₂, poor reactivity to visible light, the high recombination ratio of photoinduced electron-hole pairs, and photo corrosion, ZnO has hampered its use in photocatalysis [24]. The discovery of TiO₂ for electrochemical decomposition of water was reported in 1972 by Fujishima and Honda [25]. The authors reported that water was electrochemically decomposed to hydrogen and oxygen using connected TiO₂ and platinum electrodes under ultraviolet light. The platinum electrodes absorbed the ultraviolet light while the electron generated flows from the TiO₂ electrode onto the platinum electrode. The reduction reaction during which hydrogen was produced occurs at the cathode [26]. Later in 1977, it was reported that integrating noble metals such as platinum and gold into the electrochemical photolysis process may enhance the photoactivity of the TiO₂ [27]. Also, studies have shown that hydrogen can be produced by photogeneration on SrTiO₃ photocatalyst and the production of hydrogen and methane by photolysis of ethanol over TiO₂ and PtO₂ [28,29]. photocatalytic applications targeting only the adsorbed substances on water or air have been published by several authors [30-35]. The abundance of UV irradiation from the sun could be exploited for photocatalytic degradation [29]. A novel concept whereby a light source was employed for maintaining the TiO₂ surface as a cleaning material and photocatalysts were discovered to initiate the change in the water wettability of the TiO₂ surface before and after UV irradiation. The innovation has broadened the application of TiO₂ with a highly hydrophilic

having a stable and semi-permanent property. Fujishima and Honda, Fujishima et al., and Yamaguti and Sato [25, 26, 36] investigated the potential of electrochemical photolysis of water to identify the potential challenge of creating a photoelectrochemical tandem cell that is cost-effective, energy-efficient, and imitates natural photosynthesis. The various studies reported the application of TiO₂ in the photolysis of water. However, there is a going interest in the multifunctional capabilities of TiO₂ in photolysis applications. Obtaining intelligent and multifunctional TiO₂ materials requires designing the appropriate composition, incorporating new functional components, and modifying the pristine microstructure [20]. As a result of the large surface area of photocatalytic piers and their nearness to exhaust gases from cars, nobles metal modified photocatalysts have been reported to have a great potential to reduce poisonous gaseous emissions such as sulfur dioxide, nitrogen oxides, carbon dioxide, and so on [30, 35, 37]. As a result of the excellent photocatalytic properties, several studies have reported promising findings in the degradation of the various gaseous organic pollutants from vehicular emissions [32, 35, 38]. These photocatalysts can be categorized as self-cleaning materials with suitable physicochemical properties that can remove the products of oxidation of gaseous pollution from the surface with the help of water. In other words, the surface of TiO₂ can self-renew [39]. Moreover, TiO₂ nanoparticles possess some characteristics in terms of their nano-size, specific surface area, pore-volume, exposed surface facets, and crystalline phase content that could enhance their efficiency in photodegradation of gaseous pollutants in the air, thereby purifying it [40]. TiO₂-based catalysts have been reported mounted on asphalt pavement for air purification. Besides, Pone and Cheung (2006) reported using paving blocks that make use of NO and TiO₂ to remove waste generated. Moreover, TiO₂ nanoparticles have been reportedly used as an embedded spray for existing pavements in Italy. In another study, Hung et al. (2007) conducted a comparative analysis of the performance of different photocatalysts used in the treatment of waste obtained from cement production under ideal laboratory conditions [41]. In a similar study by Chan et al. (2009), nano-TiO₂ asphalt was applied as an environmental protection material using a permeability technique [42]. The application of modified N-doped TiO₂ photocatalysts prepared and used by spraying onto sample bituminous has been reported by Yan Hua (2010). The effectiveness of photocatalytic materials in removing pollutants such as NO_x from the atmosphere has been reported by Hassan [43]. This study, therefore, aims at delving into the various properties of TiO₂ nanoparticles and other related photocatalysts, as well as their reaction mechanisms. Besides, their applications in Civil engineering as related to asphalt mixture applications are also reviewed. The various applications of photocatalytic materials in chemical engineering were also reviewed. The various modification strategies employed to enhance the photocatalytic efficacy in the various applications were also explored in the literature and reported. Finally, the modeling of optical pavements and the influence of modifications on the fundamental properties of asphalt mixture were analyzed and reported.

Both anatase and crystallized rutile exist in quadrangular form, whereas brookite possesses a rhomboid shape. In the anatase phase of TiO₂, there exists a hierarchical symmetry of four units in every primacy cell. The rutile phase has quadrangular symmetry, possessing two equivalent units for every primary cell [50]. However, crystal symmetry has a similar form for both rutile and anatase. Due to structural constraints resulting from high thermodynamic stability, the rutile form of TiO₂ is not usually used for photocatalytic applications [51].

On the contrary, the anatase phase of TiO₂ was widely investigated for potential applications as photocatalysts due to its excellent physicochemical properties and photoactivity. The anatase phase of TiO₂ photocatalysts is highly stable in a photovoltaic reaction using an aqueous system. The anatase phase has a bandgap of 3.23 eV compared to the rutile phase with a bandgap of 2.02 eV, making the anatase TiO₂ to be widely applied in photocatalytic oxidation reactions [24]. Besides, anatase has a more suitable conduction domain for driving the photocatalytic oxidation reaction. During the photocatalytic oxidation reaction, electrons form and highly stable surface peroxide groups over the anatase.

In contrast, the rutile phase is hardly used for the photocatalytic oxidation reaction [52]. In a 1a situation, where there is a combination of both rutile and anatase in a ratio of 0.25 to 0.75, respectively, the combined phase will result in the formation of clusters or a thin rutile layer on the surface of the anatase nanoparticles. This might also lead to the formation of heterojunctions of the two crystalline phases [53]. Studies have shown that when both rutile and anatase are combined, an improvement in the photocatalytic efficiency exists compared to pristine rutile and anatase [54]. TiO₂ has been adjudged as an "ideal" semiconductor for photocatalytic processes due to its numerous advantages in degrading recalcitrant gaseous pollutants. Besides, it is inexpensive, not toxic, and very effective at low concentration and flow rate, high flow rates, high stability, excellent activity, and high removal efficiency [55-56]. These excellent properties have motivated several researchers to be involved in the use of TiO₂ for photocatalytic wastewater treatment.

Table 1: Energy band-gap (E_{bg}) with a corresponding wavelength (λ_{Ebg}) required for activation of various semiconductors [47]

Photocatalysts	Band gap(eV)	(λ _{Ebg})	Photocatalysts	Band gap(eV)	(λ _{Ebg})
Si	1.1	1127	α-Fe ₂ O ₃	3.1	400
WSe ₂	1.2	1033	ZnO	3.2	388
Fe ₂ O ₃	2.2	564	TiO ₂ (Anatase)	3.2	388
CdS	2.4	517	SrTiO ₃	3.4	365
WO ₃	2.7	459	SNO ₂	3.5	354
TiO ₂ (rutile)	3.0	413	ZnS	3.7	335



Table 2: Summary of selected Properties of TiO₂ and ZnO [47, 49]


Properties at 25 °C	TiO ₂ (Rutile)	TiO ₂ (Anatase)	ZnO
Density (g/cm ³)	4.250	3.894	5.606
Volume (nm ³ /molecule)	0.0312	0.0341	0.0241
Specific heat (J/Kmol)	55.06	55.52	43.90
Mohs hardness	7.0-7.5	5.5-6.0	4.5
Melting point (°C)	1840 (decomp.)	Trans. to. Rutile	1970 (decomp.)
Refractive index E//c	2.616	2.554	2.020
(@nD, 589nm) E/c	2.903	2.493	2.02
Relative permittivity, ε (0)	167(//c)		7.4 (lc)
Bandgap energy (eV)	3.0 (direct)	3.8 (direct)	3.4
		3.2 (indirect)	
Effective mass (hole)	20	0.8	0.24
Mobility (cm ² /Vs)	0.1	4-20	130-205
Isoelectric point	5.6	6.1	10.3

3. Principle and Mechanism of Photocatalysis

The photocatalytic reaction can be grouped into four different stages. These stages include (i) the photo-excitation process, (ii) the reduction process, (iii) the oxidation process (iv) the recombination process. As shown in Figure 2, the whole process can be explained in detail. During the photo-excitation process, there is the generation of conduction band electrons and valence band holes by the absorption of light that often corresponds to the generation rate of the conduction band and valence band holes onto the photocatalysts. In the second stage, the conduction band electrons trapping on the photocatalysts' surface. The adsorbed molecules are reduced using the trapped electrons. During the oxidation stage, the adsorbed molecules are oxidized by the valence band holes. Trapped holes are formed by the trapping of valence band holes on the photocatalysts' surface. During the recombination stage, there is a conduction band of electrons with the valence band holes. The trapped holes are also recombined with the conduction band electrons. There is also recombination of the valence band holes with the trapped electrons. And finally, the trapped holes are recombined with the trapped electrons.

During the decomposition of organic pollutants, the pathways for the primary reaction in the oxidation stage are often the reaction that occurs directly on the surface of TiO₂ with valence bands holes or trapped holes [48]. The presence of oxygen in the process generally speeds up the photocatalytic reaction. In the photocatalytic reaction, hydroxyl radicals and superoxides are responsible for oxidizing and reducing environmental contaminants [57]. There are four distinct pathways in oxidative decomposition to form OH radicals in the photocatalytic reaction. First, electrons are extracted directly through the valence band slots from the adsorbing molecules to oxidize them. In the second stage, valence band holes are superimposed on the surface of TiO₂, often resulting in trapping holes that are used to oxidize molecules on the surface of the photocatalyst. During the third stage, the surface hydroxyl groups or the water adsorbed are oxidized by the valence band openings, resulting in the generation of adsorbed hydroxyl radicals. The molecules adsorbed by OH radicals on the surface of the photocatalyst are then oxidized, causing the material to break down to form carbon dioxide and inorganic ions such as NH₄⁺, NO₃⁻, Cl⁻, and SO₄²⁻ [53, 58]. Lastly, the generated OH radicals are released from the surface to the atmosphere or into the solution. The released OH radical can then be used to oxidize the compounds far away from the photocatalyst surface. As the irradiation time increases, there is often a corresponding increase in the formation of OH radicals, leading to complete degradation of the organic pollutant as time progresses [59]. For example, consider NO_x degradation, as illustrated by Equations (1-6) [60]. The end products of the photocatalytic process are usually water-soluble nitrates [61]. These water-soluble nitrates undergo a reaction to form soluble mineral salts, which are harmless to the environment [57].

**Figure 2:** Schematic representation of the photocatalysis in a semiconductor material [62]



4. Application of Semiconductor-Titanium Dioxide

TiO₂ as a heterogeneous photocatalyst has been demonstrated to have a great potential for various applications, most especially for wastewater treatment, hydrogen production from water splitting, and photo-reforming. In addition, several studies have demonstrated the robustness of TiO₂ in the degradation of recalcitrant organic pollutants present in pharmaceutical wastewater.

4.1 General Application of Titanium Dioxide

Generally, TiO₂ is found in several industries for wide applications, such as paper production, plastic, pharmaceuticals, and sunscreen. This is due to its transparent and UV-absorbing properties. Using TiO₂ in a smart building could help in energy saving as a result of its light-reflecting qualities, which drastically reduce the amount of heat absorbed by the building. Hence, researchers (Hashimoto et al. 2005; Chen & Poon 2009) have shown dramatic energy savings through the reduction in air conditioners [63, 64]. In addition, there is an increasing research interest in the use of TiO₂ for the promotion or improvement of some properties like self-cleaning, the degradation of air and water organic pollutants, anti-fogging, anti-microbial, anti-aging, and surface cooling.

4.2 Application of Titanium Dioxide in Water Purification

Due to its interesting properties, photocatalytic degradation has been widely used to treat industrial wastewater from pharmaceuticals, refineries, and agro-allied industries. As summarized in Table 3, various modified TiO₂ have been employed to treat pharmaceutical wastewater containing organic pollutants such as chloramphenicol, metronidazole, amoxicillin trihydrate, bisphenol A, naproxen sodium, and malathion. The various studies revealed that the modified TiO₂ photocatalysts used under various conditions, such as varying irradiation time, degraded the organic pollutants to a large extent, except for Sn-TiO₂, which performed poorly in percentage removal of the organic pollutants.

4.3 Application of Titanium Dioxide in Air Purification


The various industrial activities and vehicular mobility often result in the emissions of gaseous pollutants to the environment. Among these various organic pollutants are formaldehyde, naphthalene, polycyclic aromatic hydrocarbons, trichloroethylene, tetrachloroethylene, carbon monoxide, and nitrogen dioxides have been identified as the most important air pollutants. Hence, researchers and environmentalists have focused on various strategies to reduce the impacts of these organic air pollutants on the environment. Table 4 summarizes research efforts in the last decades whereby different modified TiO₂ were applied for degrading the various organic and inorganic pollutants. The various studies revealed that the photocatalysts effectively removed over 80% of the organic pollutants from the air. The TiO₂-based photocatalysts' activities were largely dependent on several factors such as the organic pollutants concentration, air humidity and flow rate, the pollutants' nature and source of light radiation, and the physicochemical properties of the photocatalysts. As shown in Figure 3, the ultraviolet light source facilitates the degradation of the organic pollutants, thereby assisting in the decontamination of the air.

Table 3: Summary of the application of TiO₂-based photocatalysts for wastewater treatment

TiO ₂ -based photocatalysts	Organic pollutants	Irradiation time (min)	Percentage removal (%)	References
Ag-TiO ₂	Chloramphenicol (20 mg/L)	30	~100	[65]
Fe ₂ O ₃ -TiO ₂	Bisphenol	120	97	[66]
Sn-TiO ₂	Amoxicillin trihydrate (10–40 mg/L)	30	0.25	[67]
Zr-TiO ₂	Bisphenol A (15–60 mg/L)	80	100	[68]
Ni-TiO ₂	Naproxen sodium (10 mg/L)	360	84	[69]
Cu-TiO ₂	Mefenamic Acid (10 mg/L)	90	97	[70]
Fe-TiO ₂	Naproxen sodium (10 mg/L)	360	99	[69]
N-TiO ₂	Malathion (15 mg/L)	150	97	[71]
Fe-TiO ₂	4-nitrophenol (10 mg/L)	300	92	[72]
Ag-TiO ₂	Metronidazole (15–30) mg/L	120	96.55	[73]
Ag-TiO ₂	Amoxicillin (20 mg/L)	300	63.48	[74]
Cr-TiO ₂	2,4-dichlorophenol (100mg/L)	480	83	[75]
Ni-TiO ₂	Bisphenol A (10 mg/L)	120	93	[76]
S-TiO ₂	Diclofenac (10 mg/L)	240	93	[77]
N-TiO ₂	4-chlorophenoxyacetic acid (0.01–0.1 mM)	360	100	[78]
C-TiO ₂	2,4,6-trichlorophenol (10–40 mg/L)	90	98	[79]

Table 4: Summary of the application of TiO₂-based photocatalysts

TiO ₂ -based photocatalysts	Organic pollutants in air	Preparation method	References	Removal efficiency
N-Ni-TiO ₂	Formaldehyde	Sol-gel	[80]	Not mentioned
Graphene-TiO ₂	Acetone	Hydrothermal	[81]	Not mentioned
CNT/TiO ₂	Benzene	Mixing	[82]	Not mentioned
Pt/TiO ₂	Toluene	Photo-deposition	[83]	Not mentioned
Ag/TiO ₂	Toluene	Photo-deposition	[83]	Not mentioned
TiO ₂ P25	Ethylbenzene	Commercial	[84]	Not mentioned
TiO ₂ P25	o-Xylene	Commercial	[84]	Not mentioned
TiO ₂	Hexane	Sol-gel	[85]	Not mentioned
TiO ₂	Dichloromethane	Sol-gel	[41]	44%
Fe-TiO ₂	Dichloromethane	Sol-gel	[41]	65%
Pt/TiO ₂	Trichloroethylene	Photo-deposition	[83]	improving mineralization by a 3.5 time
Ag/TiO ₂	Trichloroethylene	Photo-deposition	[83]	deterredTCE photodegradation
TiO ₂	Tetrachloroethylene	Sol-gel	[86]	Not mentioned
TiO ₂ P25	2-Propanol	Commercial	[87]	Not mentioned
Pt/TiO ₂	Carbon monoxide	Mixing	[88]	Not mentioned
CdS/TiO ₂	Nitrogen oxide	Sol-gel	[47]	80%

**Figure 3:** Photocatalytic asphalt mixture [89]

The use of TiO₂ for environmental radiation has been reported to increase the span of materials and facilitate the decontamination of some industrial processes, especially in the petroleum, textile, and pharmaceutical industries. Advanced oxidation photocatalytic degradation has gained increasing interest due to its efficiency and ease of handling of the process. Besides wastewater treatment and air purification, one key application of TiO₂-based photocatalysts is the decontamination of harmful pathogens in the air. Due to the high level of contamination by pathogens, it is expedient to decontaminate indoor environments like residences and hospitals [90]. Most often, pathogens such as bacteria, viruses, and fungi are present in the air, thereby reducing the air quality, which can endanger human health. Studies have shown that TiO₂-based photocatalysts are highly efficient in photo-disinfection the various pathogen investigated.

5. Synthesis of TiO₂-Based Photocatalysts Using Different Methods

The need to expand the application of TiO₂ in various fields of photocatalysis has increased research interest in increasing the threshold wavelength of 388nm to the wavelength range within the visible light spectrum. Modifying TiO₂ photocatalysts to enhance their activities within the visible light region would enable a wider application in terms of degrading the recalcitrant organic pollutants in wastewater and air. Furthermore, the modifications of TiO₂ could further help restrain electron-hole recombination, which invariably improves photosensitivity. One major strategy to achieve this is by doping the TiO₂ with metals or non-metals. The doping of TiO₂ with metals or non-metals could be achieved either by chemical or physical ion implantation methods. Hence, the doping strategy facilitates shifting the TiO₂ absorption band toward the visible region, which can be used under natural solar irradiation [91]. The doping of TiO₂ can effectively be achieved using different synthesis methods. Various techniques have been employed for the synthesis of TiO₂-based photocatalysts that is used for various

photodegradation applications. These techniques are summarized in Table 5. These techniques include sol-gel, reverse micelle mediated sol-gel, wet impregnation, chemical reduction, microemulsion, hydrothermal, microwave mediated sol-gel, and sol-gel & hydrothermal. To increase the photoactivity of TiO_2 and enhance its ability to function effectively under visible light, various metal dopants have been employed for the synthesis. The metal dopants that have been employed include Ag, Au, Fe, Cu, Ni, Co, Mn, Zn, and Mo.

The use of the sol-gel method for the synthesis of modified TiO_2 photocatalysts has been reported by several authors such as [89, 91 - 93] used $\text{Ti}(\text{OCH}(\text{CH}_3)_2)_4$, FeCl_3 as the precursor materials for synthesizing Au- TiO_2 using sol-gel. Au composition of 0.25, 0.5, 1.0, 2.0, 4.0, and 5.0 atomic% were employed for the modification of the Au- TiO_2 . Also, [94] employed TiCl_4 , C_2MnO_4 , TiCl_4 , C_2ZnO_4 , and $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ as precursor materials for synthesizing Mn- TiO_2 and Zn- TiO_2 , and Ni- TiO_2 photocatalysts by sol-gel method. The effect of varying the concentration of the Mn, Zn, and Ni dopants on the photoactivity of the TiO_2 was also investigated. Similarly, [91] also used $\text{Ti}(\text{OCH}(\text{CH}_3)_2)_4$, $\text{Cu}(\text{CO}_2\text{CH}_3)_2$ as precursors materials for the synthesis of Cu- TiO_2 using the sol-gel method. The Cu dopant's concentration of 5.9 and 13 mol% was used to determine its effect on the TiO_2 photoactivity. Ali et al. (2018) employed Titanium tetra-isopropoxide, silver nitrate, glacial acetic acid, and absolute ethanol to prepare TiO_2 and Ag- TiO_2 photocatalysts. The concentration of 2, 4, 6, and 8 mol% was used for the Ag synthesis to determine the photoactivity effect [92]. Modified forms of sol-gel, such as reverse micelle-mediated sol-gel, microwave-mediated sol-gel, and combined sol-gel-hydrothermal methods, have also been employed to synthesize Ag- TiO_2 Cu- TiO_2 and Bi- TiO_2 photocatalysts. Precursors such as $\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, AgNO_3 , TiCl_4 , C_2NiO_4 , $\text{Ti}(\text{OCH}(\text{CH}_3)_2)_4$, $\text{Bi}(\text{NO}_3)_3 \cdot 5\text{H}_2\text{O}$ were employed for the synthesis of the photocatalysts with varying concentrations of dopants.

Besides the sol-gel method, wet-impregnation of the metal precursors into the TiO_2 has been reported by Tayade et al. (2006) for the synthesis of Ag- TiO_2 , Fe- TiO_2 , and Ni- TiO_2 using $\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, AgNO_3 , TiO_2 (Degussa P25), $\text{Cu}(\text{NO}_3)_2$, and CoSO_4 , TiOSO_4 as precursors. Furthermore, the effect of varying the Ag, Fe, and Cu dopants on the TiO_2 photoactivity was also investigated [93].

Table 5: Summary of synthesis techniques employed for TiO_2 -based photocatalysts

TiO_2 -based photocatalyst	Preparation methods	Chemicals	References
Ag- TiO_2	Sol-gel	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, AgNO_3	[92]
Ag- TiO_2	Reverse micelle mediated sol-gel	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, AgNO_3	[95]
Ag- TiO_2	Wet impregnation	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, AgNO_3	[8]
Ag- TiO_2	Chemical reduction	TiO_2 powder, AgNO_3	[96]
Ag- TiO_2	Microemulsion	$(\text{Ti}(\text{OC}_4\text{H}_9)_4)$, $\text{HAuCl}_4 \cdot 4\text{H}_2\text{O}$	[97]
Au- TiO_2	Photolysis	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, FeCl_3	[98]
Fe- TiO_2	Wet impregnation	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$	[8]
Fe- TiO_2	Hydrothermal	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, CuCl_2	[99]
Cu- TiO_2	Sol-gel	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, $\text{Cu}(\text{CO}_2\text{CH}_3)_2$	[91]
Cu- TiO_2	Wet impregnation	TiO_2 (Degussa P25), $\text{Cu}(\text{NO}_3)_2$	[8]
Cu- TiO_2	Microwave mediated sol-gel	TiCl_4 , C_2NiO_4	[100]
Ni- TiO_2	Sol-gel	Commercial TiO_2 , $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$	[94]
Ni- TiO_2	Hydrothermal	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, $\text{Ni}(\text{OCOCH}_3)_2 \cdot 4\text{H}_2\text{O}$	[101]
Ni- TiO_2	Wet impregnation	CoSO_4 , TiOSO_4	[8]
Co- TiO_2	Hydrothermal	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, CoCl_2	[102]
Co- TiO_2	Wet impregnation	CoSO_4 , TiOSO_4	[8]
Bi- TiO_2	Sol-gel & hydrothermal	$\text{Ti}\{\text{OCH}(\text{CH}_3)_2\}_4$, $\text{Bi}(\text{NO}_3)_3 \cdot 5\text{H}_2\text{O}$	[103]
Mn- TiO_2	Sol-gel	TiCl_4 , C_2MnO_4	[94]
Zn- TiO_2	Sol-gel	TiCl_4 , C_2ZnO_4	[94]



Figure 4: (a) The TiO_2 solution spraying process (b) the painting process of TiO_2 solution [43]

6. Conclusions

The study has presented an overview of the modification of TiO₂ photocatalysts used for various applications such as air purification and wastewater treatment. The distinctive properties of TiO₂ and modified TiO₂ make it suitable for air purification and wastewater treatment application. The various studies have revealed that TiO₂ has been modified with different metals and non-metals. The physicochemical properties of the modified TiO₂ strongly depend on the composition of the photocatalysts, the type of synthesis methods, and the nature of dopants. Out of the various synthesis methods used for synthesizing the modified TiO₂, the sol-gel was commonly used and found effective compared to other methods such as wet impregnation, hydrothermal, and chemical reduction. On the other hand, the TiO₂ doped with noble metals was very effective in degrading the air and water pollutants. This can be attributed to the distinctive physicochemical and photo properties of the TiO₂-based catalysts. Although the various modified TiO₂ has been proven effective for degrading the various air and water pollutant, there is a need for continuous strategies to improve the properties of TiO₂-based catalysts for effective mitigations of environmental pollutants from the environment.

Acknowledgment

The authors are grateful to the Chemical Engineering Department, University of Technology, for providing space and facilities to conduct this work.

Author contribution

All authors contributed equally to this work.

Funding

This research received no external funding.

Data availability statement

The data that support the findings of this study are available on request from the corresponding author.

Conflicts of interest

Authors declare that their present work has no conflict of interest with other published works.

References:

- [1] O. G. Fawole, X.-M. Cai, and A. R. MacKenzie, Gas flaring and resultant air pollution: A review focusing on black carbon. *Environ. Pollut.*, 216 (2016) 182–197. doi.org/10.1016/j.envpol.2016.05.075
- [2] A. R. Ridzuan, The impact of energy consumption based on fossil fuel and hydroelectricity generation towards pollution in Malaysia, Indonesia and Thailand. *Int. J. Energy Econ. Policy*, 10 (2020) 215–227. doi.org/10.32479/ijeep.8140.
- [3] W. M. Sweileh, S. W. Al-Jabi, S. H. Zyoud, and A. F. Sawalha, Outdoor air pollution and respiratory health: A bibliometric analysis of publications in peer-reviewed journals (1900 - 2017). *Multidisciplinary Res. Medic.*, 13 (2018) 1–12. doi.org/10.1186/s40248-018-0128-5.
- [4] S. Jiménez, M. M. Micó, M. Arnaldos, F. Medina, and S. Contreras, State of the art of produced water treatment. *Chemosphere.*, 192 (2018) 186–208. doi.org/https://doi.org/10.1016/j.chemosphere.2017.10.139
- [5] S. Varjani, R. Joshi, V. K. Srivastava, H. H. Ngo, and W. Guo, Treatment of wastewater from petroleum industry: current practices and perspectives. *Envir. Sci. and Pollution. Res.*, 27 (020) 27172–27180. doi.org/10.1007/s11356-019-04725-x.
- [6] T. Y. Wu, A. W. Mohammad, J. M. Jahim, and N. Anuar, Pollution control technologies for the treatment of palm oil mill effluent (POME) through end-of-pipe processes. *J. Environ. Manage.*, 91 (2020) 1467–1490. doi.org/10.1016/j.jenvman.2010.02.008
- [7] Y. Wang, X. Luo, W. Chen, M. Zhao, and B. Wang, Exploring the spatial effect of urbanization on multi-sectoral CO₂ emissions in China. *Atmo.Pollution Res.*, 10 (2019) 1610–1620. doi.org/10.1016/j.apr.2019.06.001
- [8] R. J. Tayade, and D. L. Key, Synthesis and Characterization of Titanium Dioxide Nanotubes for Photocatalytic Degradation of Aqueous Nitrobenzene in the Presence of Sunlight. *Materials Sci. Forum*, 657 (2010) 62–74. https://doi.org/10.4028/www.scientific.net/MSF.657.62
- [9] P. Amoatey, H. Omidvarborna, M. S. Baawain, and A. Al-Mamun, Emissions and exposure assessments of SOX, NOX, PM10/2.5 and trace metals from oil industries: A review study (2000–2018). *Proc. Safety and Env. Protection*, 123 (2019) 215–228. doi.org/10.1016/j.psep.2019.01.014.
- [10] M. Salman, X. Long, L. Dauda, C. N. Mensah, and S. Muhammad, Different impacts of export and import on carbon emissions across 7 ASEAN countries: A panel quantile regression approach. *Sci.of the Total Env.*, 686 (2019) 1019–1029. doi.org/10.1016/j.scitotenv.2019.06.019

- [11] M. F. Abid, E. M. Mohammed, O. N. Abdullah, Designing and operating a pilot plant for purification of industrial wastewater from toxic organic compounds by utilizing solar energy. *Korean J. Chem. Eng.*, 31(2014) 1194-1203. DOI: 10.1007/s11814-014-0052-0.
- [12] A. Sobczyński, L. Duczmal, and W. Zmudziński, Phenol destruction by photocatalysis on TiO₂: An attempt to solve the reaction mechanism. *J. Mol. Catal. A Chem.*, 213 (2004) 225–230. doi.org/10.1016/j.molcata.2003.12.006
- [13] V. Kumaravel, S. Mathew, J. Bartlett, and S. C. Pillai, Photocatalytic hydrogen production using metal doped TiO₂: A review of recent advances. *Applied Catalysis B: Env.J.*, 244 (2018), 1021–1064. doi.org/10.1016/j.apcatb.2018.11.080.
- [14] Alasady, A. M. Abdullah, Solar energy the suitable energy alternative for Iraq beyond oil. 2011 International Conference on Petroleum and Sustainable Development, 26, 2011, 11–15.
- [15] J. Qian, Z. Chen, C. Liu, X. Lu, F. Wang, and M. Wang, Improved visible-light-driven photocatalytic activity of CeO₂ microspheres obtained by using lotus flower pollen as biotemplate. *Mater. Sci.in Semiconductor Processing*, 25(2014) 27–33. doi.org/10.1016/j.mssp.2013.09.020.
- [16] G. Li, J. Guo, Y. Hu, Y. Wang, J. Wang, S. Zhang, and Q. Zhong, Facile synthesis of the Z-scheme graphite-like carbon nitride/silver/silver phosphate nanocomposite for photocatalytic oxidative removal of nitric oxides under visible light. *J. of Colloid and Inter. Sci.*, 588 (2021)110–121. doi.org/10.1016/j.jcis.2020.12.063.
- [17] D. Praveen Kumar, N. Lakshmana Reddy, B. Srinivas, V. Durgakumari, V. Roddatis, O. Bondarchuk, M. Karthik, Y. Ikuma, and M. V. Shankar, Stable and active CuxO/TiO₂ nanostructured catalyst for proficient hydrogen production under solar light irradiation. *Sol. Energy Mater. Sol. Cells.*, 146 (2016) 63–71. doi.org/10.1016/j.solmat.2015.11.030.
- [18] M.F. Abid, S.T. Hamiedi, S.I. Ibrahim, S.K. Al-Nasri, Removal of toxic organic compounds from synthetic wastewater by a solar photocatalysis system. *Desal. and Water Treat.*, 105 (2018) 119–125. doi: 10.5004/dwt.2018.22017.
- [19] C. A. Marti, and S. Ferro, Electrochemical oxidation of organic pollutants for the wastewater treatment : direct and indirect processes. *Chem. Soci. Reviews*, 35 (2006) 1324–1340. doi.org/10.1039/b517632h.
- [20] M. Ge, J. Cai, J. Iocozzia, C. Cao, J. Huang, X. Zhang, J. Shen, S. Wang, S. Zhang, K. Q. Zhang, Y. Lai, and Z. Lin, A review of TiO₂ nanostructured catalysts for sustainable H₂ generation. *Inter. J. of Hydrogen Energy*, 42 (2017) 8418–8449. doi.org/10.1016/j.ijhydene.2016.12.052
- [21] S. B. Patil, P. S. Basavarajappa, N. Ganganagappa, M. S. Jyothi, A. V Raghu, and K. R. Reddy, Recent advances in non-metals-doped TiO₂ nanostructured photocatalysts for visible-light driven hydrogen production, CO₂ reduction and air purification. *Int. J. Hydrogen Energy*, 44 (2019) 13022–13039. doi.org/10.1016/j.ijhydene.2019.03.164.
- [22] Blengini, G. A., El Latunussa, C., Eynard, U., de Matos, C. T., Wittmer, D. M. A. G., Georgitzikis, K., ... & Pennington, D. W. (2020). *Study on the EU's List of Critical Raw Materials (2020)*. Publications Office of the European Union.
- [23] K. P. Jyothi, S. Yesodharan, and E. P. Yesodharan, Ultrasound (US), Ultraviolet light (UV) and combination (US+UV) assisted semiconductor catalysed degradation of organic pollutants in water: Oscillation in the concentration of hydrogen peroxide ford in situ. *Ultrasonics Sonochemistry*, 21(2014)1787–1796. doi.org/10.1016/j.ultsonch.2014.03.019
- [24] D. Chen, K. Wang, D. Xiang, R. Zong, W. Yao, and Y. Zhu, Significantly enhancement of photocatalytic performances via core–shell structure of ZnO@ mpg-C₃N₄. *Applied Catalysis B: Envir.J.*, 147(2014) 554-561.
- [25] A. Fujishimma, and K. Honda, Electrochemical Photolysis of Water at a Semiconductor Elect..*Nat.*, 238 (1972) 37–38. doi.org/10.1038/238037a0.
- [26] A. Fujishima, K. Kohayakawa, and K. Honda, Hydrogen Production under Sunlight with an Electrochemical Photocell. *J. of The Electr. Soci.*, 122 (1975) 1487–1489. doi.org/10.1149/1.2134048.
- [27] T. Inoue, T. Watanabe, A. Fujishima, and K. Honda, Competitive photosensitized oxidation at tio2 photoanode. *Chemistry Letters*, 6 (1977) 1073–1076.
- [28] M. P. Languer, F. R. Scheffer, A. F. Feil, D. L. Baptista, P. Migowski, G. J. Machado, D. P. de Moraes, J. Dupont, S. R. Teixeira, and D. E. Weibel, Photo-induced reforming of alcohols with improved hydrogen apparent quantum yield on TiO₂ nanotubes loaded with ultra-small Pt nanoparticles. *Inter. J. of Hydrogen Energy*, 38 (2013)14440–14450. doi.org/10.1016/j.ijhydene.2013.09.018
- [29] S. K. Parayil, H. S. Kibombo, C.-M. Wu, R. Peng, T. Kindle, S. Mishra, S. P. Ahrenkiel, J. Baltrusaitis, N. M. Dimitrijevic, T. Rajh, and R. T. Koodali, Synthesis-Dependent Oxidation State of Platinum on TiO₂ and Their Influences on the Solar Simulated Photocatalytic Hydrogen Production from Water. *J. of Physical Chem. C*, 117(2013) 16850–16862. doi.org/10.1021/jp405727k.
- [30] G. Hüskén, M. Hunger, and H. J. H. Brouwers, Experimental study of photocatalytic concrete products for air purification. *Build. and Envir.*, 44 (2009) 2463–2474. doi.org/10.1016/j.buildenv.2009.04.010

- [31] C.-C. Lo, C.-W. Huang, C.-H. Liao, and J. C. S. Wu, Novel twin reactor for separate evolution of hydrogen and oxygen in photocatalytic water splitting. *Inter. J. of Hydrogen Energy*, 35 (2010) 1523–1529. doi.org/10.1016/j.ijhydene.2009.12.032.
- [32] A. H. Mamaghani, F. Haghghat, and C.-S. Lee, Photocatalytic oxidation technology for indoor environment air purification: The state-of-the-art. *Applied Catalysis B: Envir.J.*, 203 (2017) 247–269. doi.org/10.1016/j.apcatb.2016.10.037.
- [33] F. Mushtaq, A. Asani, M. Hoop, X.Z. Chen, D. Ahmed, B. J. Nelson, and S. Pané, Highly Efficient Coaxial TiO₂-PtPd Tubular Nanomachines for Photocatalytic Water Purification with Multiple Locomotion Strategies. *Advan. Fun. Materials*, 26 (2016) 6995–7002. doi.org/10.1002/adfm.201602315
- [34] N. Negishi, Y. Miyazaki, S. Kato, and Y. Yang, Effect of HCO₃⁻ concentration in groundwater on TiO₂ photocatalytic water purification. *Applied Catalysis B: Envir.J.*, 242 (2019) 449–459. doi.org/10.1016/j.apcatb.2018.10.022.
- [35] H. Ren, P. Koshy, W.F. Chen, S. Qi, and C. C. Sorrell, Photocatalytic materials and technologies for air purification. *J. of Hazar. Materials*, 325 (2017) 340–366. doi.org/10.1016/j.jhazmat.2016.08.072
- [36] K. Yamaguti, and S. Sato, Photolysis of water over metallized powdered titanium dioxide. *J. Chem. Soc.{,} Faraday Trans. 1*, 81 (1985) 1237–1246. doi.org/10.1039/F19858101237
- [37] A. N. Banerjee, The design, fabrication, and photocatalytic utility of nanostructured semiconductors: Focus on TiO₂-based nanostructures. *Nanotechnology, Scie.and Appli.*, 4 (2011) 35–65. doi.org/10.2147/NSA.S9040.
- [38] C. Nie, L. Liu, and R. He, Pt/TiO₂-ZnO in a circuit Photo-electro-catalytically removed HCHO for outstanding indoor air purification. *Separ.and Puri. Technology*, 206 (2018) 316–323. doi.org/10.1016/j.seppur.2018.06.024
- [39] I. B. Topçu, E. Akkan, T. Uygunoğlu, and K. Çalışkan, Self-Cleaning Concretes: An Overview. *J. Cem. Based Compos*, 2 (2020) 6-12.
- [40] K. Nakata, and A. Fujishima, TiO₂ photocatalysis: Design and applications. *J. of photochemistry and photobiology C: Photochemistry Reviews*, 13 (2012) 169-189. doi.org/10.1016/j.jphotochemrev.2012.06.001
- [41] W.C. Hung, S.H. Fu, J.J. Tseng, H. Chu, and T.H. Ko, Study on photocatalytic degradation of gaseous dichloromethane using pure and iron ion-doped TiO₂ prepared by the sol-gel method. *Chemosphere*, 66 (2007) 2142–2151. doi.org/10.1016/j.chemosphere.2006.09.037
- [42] K. H. Chan, and W. Chu, Degradation of atrazine by cobalt-mediated activation of peroxydisulfate: different cobalt counteranions in homogenous process and cobalt oxide catalysts in photolytic heterogeneous process. *Water Res.*, 43 (2009) 2513-2521.
- [43] M. Hassan, L. N. Mohammad, S. Asadi, H. Dylla, and S. Cooper, Sustainable photocatalytic asphalt pavements for mitigation of nitrogen oxide and sulfur dioxide vehicle emissions. *J. of Materials in Civil Eng.*, 25 (2013) 365-371.
- [44] A. Mittal, B. Mari, S. Sharma, V. Kumari, S. Maken, K. Kumari, and N. Kumar, Non-metal modified TiO₂: a step towards visible light photocatalysis. *Journal of Materials Science: Mater. in Electr.*, 30 (2019) 3186-3207.
- [45] G. Crini, Non-conventional low-cost adsorbents for dye removal: a review. *Bioresource tech. J.*, 97(2006) 1061-1085.
- [46] M. T. Yagub, T. K. Sen, S. Afroz, and H. M. Ang, Dye and its removal from aqueous solution by adsorption: a review. *Advan.in colloid and inter. sci.*, 209 (2014) 172-184.
- [47] A. Y. Zhang, W. K. Wang, D. N. Pei, and H. Q. Yu, Degradation of refractory pollutants under solar light irradiation by a robust and self-protected ZnO/CdS/TiO₂ hybrid photocatalyst. *Water res.J.*, 92 (2016) 78-86.
- [48] I. Rocha Segundo, E. Freitas, S. Landi, M. F. Costa, and J. O. Carneiro, Smart, photocatalytic and self-cleaning asphalt mixtures: a literature review. *Coatings*, 9 (2019) 696.
- [49] H. Chen, Y. Liu, C. Xie, J. Wu, D. Zeng, and Y. Liao, A comparative study on UV light activated porous TiO₂ and ZnO film sensors for gas sensing at room temperature. *Ceramics Inter.J.*, 38 (2012) 503-509.
- [50] C. L. Bianchi, C. Pirola, M. Stucchi, B. Sacchi, G. Cerrato, S. Morandi, ... and V. A. Capucci, new frontier of photocatalysis employing micro-sized TiO₂: Air/water pollution abatement and self-cleaning/antibacterial applications 635-666, 2016. INTECH OPEN.
- [51] F. Sandrolini, E. Franzoni, and M. Biolcati Rinaldi, Proposte per una metodologia di valutazione dell'ecosostenibilità dei materiali e componenti edilizi in sede progettuale. *INARCOS*, 634, 637-640, 2002.
- [52] J. Zhang, Y. Wu, M. Xing, S. A. K. Leghari, and S. Sajjad, Development of modified N doped TiO₂ photocatalyst with metals, nonmetals and metal oxides. *Energy & Envir. Sci.*, 3 (2010) 715-726. doi.org/10.1039/B927575D.
- [53] X. Jiang, M. Manawan, T. Feng, R. Qian, T. Zhao, G. Zhou, ... and J. H. Pan, Anatase and rutile in evonik aerioxide P25: heterojunctioned or individual nanoparticles?. *Catalysis Today*, 300 (2018) 12-17. doi.org/10.1016/j.cattod.2017.06.010

- [54] A. O. Ibhaddon, and P. Fitzpatrick, Heterogeneous photocatalysis: recent advances and applications. *Catalysts*, 3 (2013) 189-218. doi.org/10.3390/catal3010189.
- [55] M. Sayed, A. Arooj, N. S. Shah, J. A. Khan, L. A. Shah, F. Rehman, ... and A. R. Khan, Narrowing the band gap of TiO₂ by co-doping with Mn²⁺ and Co²⁺ for efficient photocatalytic degradation of enoxacin and its additional peroxidase like activity: a mechanistic approach. *J. of Mol. Liq.*, 272 (2018) 403-412.
- [56] A. A. Septevani, Y. A. Devy, D. S. Khaerudini, M. Septiyanti, and Y. Sampora, (2021, August). Facile and low-cost production of TiO₂ nanoparticles using high-energy milling for dye degradation." *AIP Conference Proceedings*. Vol. 2382. No. 1. AIP Publishing LLC, 2021.
- [57] M. Hassan and A. M. Okeil, Field and laboratory investigation of photocatalytic pavements (No. GCCETR 11-10) 2011. Gulf Coast Research Center for Evacuation and Transportation Resiliency.
- [58] G. Oksdath-Mansilla, A. B. Peññory, I. Barnes, P. Wiesen, and M. A. Teruel, Photodegradation of (CH₃CH₂)₂S and CH₃CH₂SCH₃ initiated by OH radicals at atmospheric pressure. Product yields and mechanism in NO_x free air. *Atmos. Envir.*, 55 (2012) 263-270. doi.org/10.1016/j.atmosenv.2012.02.086.
- [59] L. Venturini, and M. Bacchi, Research, Design, and Development of a Photocatalytic Asphalt Pavement. *Proceedings of 2nd I. Conf. on Envir. Friendly Roads: ENVIROAD 2009*, Warsaw, Poland, 2009.
- [60] J. M. Cordero, R. Hingorani, E. Jiménez-Relinque, M. Grande, R. Borge, A. Narros, and M. Castellote, NO_x removal efficiency of urban photocatalytic pavements at pilot scale. *Science of The Total Envir.*, 719 (2020) 137459.
- [61] M. Bocci, G. Cerni, and S. Colagrande, Experimental investigation of the dynamic behaviour of asphalt concrete treated with photocatalytic mortars. In *Proceedings of the 3rd International Conference on Transportation Infrastructure 95-102*, 2014.
- [62] T. Feng, G. S. Feng, L. Yan, and J. H. Pan, One-dimensional nanostructured TiO₂ for photocatalytic degradation of organic pollutants in wastewater. *International Journal of Photoenergy*, 2014.
- [63] K. Hashimoto, H. Irie, and A. Fujishima, TiO₂ photocatalysis: a historical overview and future prospects. *Japanese journal of applied physics*, 44 (2005) 8269.
- [64] J. Chen, and C. S. Poon, Photocatalytic construction and building materials: from fundamentals to applications. *Building and environment*, 44 (2009) 1899-1906.
- [65] M. Shokri, A. Jodat, N. Modirshahla, and M. A. Behnajady, Photocatalytic degradation of chloramphenicol in an aqueous suspension of silver-doped TiO₂ nanoparticles. *Environmental technology*, 34 (2013) 1161-1166.
- [66] A. M. Sheikh Asadi, M. Malakootian, E. Kowsari, and H. Alidadi, Ionic liquid-assisted sol-gel synthesis of Fe₂O₃-TiO₂ for enhanced photocatalytic degradation of bisphenol a under UV illumination: Modeling and optimization using response surface methodology. *Optik*, 204 (2020) 164229. doi.org/10.1016/j.ijleo.2020.164229.
- [67] R. Mohammadi, B. Massoumi, and M. Rabani, Photocatalytic Decomposition of Amoxicillin Trihydrate Antibiotic in Aqueous Solutions under UV Irradiation Using Sn/TiO₂ Nanoparticles. *I. J. of Photoenergy*, (2012) 514856. doi.org/10.1155/2012/514856.
- [68] Y. Li, W. Gao, L. Ci, C. Wang, and P. M. Ajayan, Catalytic performance of Pt nanoparticles on reduced graphene oxide for methanol electro-oxidation. *Carbon*, 48 (2010) 1124-1130. doi.org/10.1016/j.carbon.2009.11.034
- [69] M. Hinojosa – Reyes, R. Camposeco – Solis, F. Ruiz, V. Rodríguez – González, and E. Moctezuma, Promotional effect of metal doping on nanostructured TiO₂ during the photocatalytic degradation of 4-chlorophenol and naproxen sodium as pollutants. *Materials Sci. in Semiconductor Process.*, 100 (2019) 130-139. doi.org/10.1016/j.mssp.2019.04.050.
- [70] Z.Y. Shanian, M.F. Abid, K.A. Sukkar, Photodegradation of mefenamic acid from wastewater in a continuous flow solar falling film reactor. *Desali. and Water Treat.*, 210 (2021) 22-30. doi: 10.5004/dwt.2021.26581.
- [71] A. N. Kadam, R. S. Dhabbe, M. R. Kokate, Y. B. Gaikwad, and K. M. Garadkar, Preparation of N doped TiO₂ via microwave-assisted method and its photocatalytic activity for degradation of Malathion. *Spectrochimica Acta Part A: Mole. and Biomolecular Spectroscopy*, 133 (2014) 669-676.
- [72] S. Sood, A. Umar, S. K. Mehta, and S. K. Kansal, Highly effective Fe-doped TiO₂ nanoparticles photocatalysts for visible-light driven photocatalytic degradation of toxic organic compounds. *J. of colloid and inter. Sci.*, 450 (2015) 213-223.
- [73] S. S. Boxi, K. Mukherjee, and S. Paria, Ag doped hollow TiO₂ nanoparticles as an effective green fungicide against *Fusarium solani* and *Venturia inaequalis* phytopathogens. *Nanotechnology*, 27 (2016) 085103.
- [74] K. H. Leong, B. L. Gan, S. Ibrahim, and P. Saravanan, Synthesis of surface plasmon resonance (SPR) triggered Ag/TiO₂ photocatalyst for degradation of endocrine disturbing compounds. *Applied Surf. Sci.*, 319 (2014) 128-135.

- [75] S. Mahdavi, and S. R. Allahkaram, Composition, characteristics and tribological behavior of Cr, Co–Cr and Co–Cr/TiO₂ nano-composite coatings electrodeposited from trivalent chromium based baths. *J. of Alloys and Comp.*, 635 (2015) 150–157. doi.org/10.1016/j.jallcom.2015.02.119
- [76] M. P. Blanco-Vega, J. L. Guzmán-Mar, M. Villanueva-Rodríguez, L. Maya-Treviño, L. L. Garza-Tovar, A. Hernández-Ramírez, and L. Hinojosa-Reyes, Photocatalytic elimination of bisphenol A under visible light using Ni-doped TiO₂ synthesized by microwave assisted sol-gel method. *Materials Sci. in Semiconductor Process.*, 71 (2017) 275–282. doi.org/10.1016/j.mssp.2017.08.013
- [77] Y. X. Li, X. Wang, C. C. Wang, H. Fu, Y. Liu, P. Wang, and C. Zhao, S-TiO₂/UiO-66-NH₂ composite for boosted photocatalytic Cr (VI) reduction and bisphenol A degradation under LED visible light. *J. of Hazard. Materials*, 399 (2020) 123085.
- [78] A. Abdelhaleem, and W. Chu, Photodegradation of 4-chlorophenoxyacetic acid under visible LED activated N-doped TiO₂ and the mechanism of stepwise rate increment of the reused catalyst. *J. of Hazard. Materials*, 338 (2017) 491–501. doi.org/10.1016/j.jhazmat.2017.05.056
- [79] A. B. Lavand, and Y. S. Malghe, Synthesis, characterization and visible light photocatalytic activity of nitrogen-doped zinc oxide nanospheres. *J. of Asian Ceramic Socie.*3 (2015) 305–310. doi.org/10.1016/j.jascer.2015.06.002.
- [80] L.W. Zhang, H.B. Fu, and Y.F. Zhu, Efficient TiO₂ Photocatalysts from Surface Hybridization of TiO₂ Particles with Graphite-like Carbon. *Advan. Funct. Materials*, 18 (2008) 2180–2189. doi.org/10.1002/adfm.200701478.
- [81] W. Wang, J. Yu, Q.Xiang, and B. Cheng, Enhanced photocatalytic activity of hierarchical macro/mesoporous TiO₂–graphene composites for photodegradation of acetone in air. *Applied Catalysis B: Envir.*, 119–120 (2012)109–116. doi.org/10.1016/j.apcatb.2012.02.035
- [82] Y.J. Xu, Y. Zhuang, and X. Fu, New Insight for Enhanced Photocatalytic Activity of TiO₂ by Doping Carbon Nanotubes: A Case Study on Degradation of Benzene and Methyl Orange. *The J. of Physical Chem. C*, 114 (2010) 2669–2676. doi.org/10.1021/jp909855p
- [83] C. Young, T. M. Lim, K. Chiang, J. Scott, and R. Amal, Photocatalytic oxidation of toluene and trichloroethylene in the gas-phase by metallised (Pt, Ag) titanium dioxide. *Applied Catalysis B: Envir.*, 78 (2008) 1–10. doi.org/10.1016/j.apcatb.2007.08.011
- [84] A. Strini, S. Cassese, and L. Schiavi, Measurement of benzene, toluene, ethylbenzene and o-xylene gas phase photodegradation by titanium dioxide dispersed in cementitious materials using a mixed flow reactor. *Applied Catalysis B: Environmental*, 61(2005) 90–97. doi.org/10.1016/j.apcatb.2005.04.009
- [85] L. ZHANG, P. LI, Z. GONG, and A. A. Oni, Photochemical behavior of benzo[a]pyrene on soil surfaces under UV light irradiation. *Journal of Environmental Sciences*, 18 (2006) 1226–1232. doi.org/10.1016/S1001-0742(06)60067-3
- [86] S. Yamazaki, H. Tsukamoto, K. Araki, T. Tanimura, I. Tejedor-Tejedor, and M. A. Anderson, Photocatalytic degradation of gaseous tetrachloroethylene on porous TiO₂ pellets. *Applied Catalysis B: Envir.*, 33(2001) 109–117. doi.org/10.1016/S0926-3373(01)00167-9
- [87] J. Araña, O. González Díaz, M. Miranda Saracho, J. M. Doña Rodríguez, J. A. Herrera Melián, and J. Pérez Peña, Photocatalytic degradation of formic acid using Fe/TiO₂ catalysts: the role of Fe₃₊/Fe₂₊ ions in the degradation mechanism. *Applied Catalysis B: Envir.*, 32 (2001) 49–61. doi.org/10.1016/S0926-3373(00)00289-7.
- [88] Y. Li, Y. Xie, S. Peng, G. Lu, and S. Li, Photocatalytic hydrogen generation in the presence of chloroacetic acids over Pt/TiO₂. *Chemosphere*, 63 (2006) 1312-1318.
- [89] S. Shen, M. Burton, B. Jobson, and L. Haselbach, Pervious concrete with titanium dioxide as a photocatalyst compound for a greener urban road environment. *Constr. and Building Materials*, 35 (2012) 874- 883.
- [90] V. Binas, D. Venieri, D. Kotzias, and G. Kiriakidis, Modified TiO₂ based photocatalysts for improved air and health quality. *J. of Materiomics*, 3 (2017) 3-16.
- [91] V. Krishnakumar, S. Boobas, J. Jayaprakash, M. Rajaboopathi, B. Han, and M. Louhi-Kultanen, Effect of Cu doping on TiO₂ nanoparticles and its photocatalytic activity under visible light. *J. of Materials Sci.: Materials in Electronics*, 27 (2016) 7438–7447. doi.org/10.1007/s10854-016-4720-1.
- [92] T. Ali, A. Ahmed, U. Alam, I. Uddin, P. Tripathi, and M. Muneer, Enhanced photocatalytic and antibacterial activities of Ag-doped TiO₂ nanoparticles under visible light. *Materials Chem. and Phys.*, 212 (2018) 325–335. doi.org/10.1016/j.matchemphys.2018.03.052
- [93] K. S. Wang, K. Y. Chiang, C. C. Tsai, C. J. Sun, C. C. Tsai, and K. L. Lin, The effects of FeCl₃ on the distribution of the heavy metals Cd, Cu, Cr, and Zn in a simulated multimetal incineration system. *Envir. I.*, 26 (2001) 257-263.

- [94] L. G. Devi, B. N. Murthy, and S. G. Kumar, Photocatalytic activity of TiO₂ doped with Zn²⁺ and V⁵⁺ transition metal ions: Influence of crystallite size and dopant electronic configuration on photocatalytic activity. *Mater. Sci. and Eng.: B*, 166 (2010) 1–6. doi.org/10.1016/j.mseb.2009.09.008.
- [95] S. Angkaew, and P. Limsuwan, Preparation of silver-titanium dioxide core-shell (Ag@ TiO₂) nanoparticles: Effect of Ti-Ag mole ratio. *Procedia Engineering*, 32 (2012) 649-655.
- [96] K. H. Ng, C. H. Lee, M. R. Khan, and C. K. Cheng, Photocatalytic degradation of recalcitrant POME waste by using silver doped titania: Photokinetics and scavenging studies. *Chem. Eng. J.*, 286 (2016) 282–290. doi.org/10.1016/j.cej.2015.10.072
- [97] A. Zielińska, E. Kowalska, J. W. Sobczak, I. Łącka, M. Gazda, B. Ohtani, J. Hupka, and A. Zaleska, Silver-doped TiO₂ prepared by microemulsion method: Surface properties, bio- and photoactivity. *Sep. and Purif. Techn.*, 72 (2010) 309–318. doi.org/10.1016/j.seppur.2010.03.002
- [98] H. M. Zaid, Photodegradation of methylene blue solution via au doped TiO₂ nanocomposite catalysts prepared using novel photolysis method. *Iranian J. of Chemistry and Chem. Eng.*, 38 (2019) 20–35.
- [99] A. El Mragui, Y. Logvina, L. da Silva, Zegaoui, O., and J. C. G. da Silva, Synthesis of Fe- and Co-Doped TiO₂ with Improved Photocatalytic Activity Under Visible Irradiation Toward Carbamazepine Deg.. *Materials*, 12 (23). doi.org/10.3390/ma12233874.
- [100] L.F. Chiang, and R.A. Doong, Cu–TiO₂ nanorods with enhanced ultraviolet- and visible-light photoactivity for bisphenol A degradation. *J. of Hazard. Materials*, 277 (2014) 84–92. doi.org/10.1016/j.jhazmat.2014.01.047
- [101] G. G. Nakhate, V. S. Nikam, K. G. Kanade, S. Arbuji, B. B. Kale, and J. O. Baeg, Hydrothermally derived nanosized Ni-doped TiO₂: A visible light driven photocatalyst for methylene blue degradation. *Materials Chem. and Physics*, 124 (2010) 976–981. doi.org/10.1016/j.matchemphys.2010.08.007.
- [102] L. Jiang, Y. Huang, and T. Liu, Enhanced visible-light photocatalytic performance of electrospun carbon-doped TiO₂/halloysite nanotube hybrid nanofibers. *J. of Colloid and Inter. Sci.*, 439 (2015) 62–68. doi.org/10.1016/j.jcis.2014.10.026
- [103] T. S. Natarajan, K. Natarajan, H. C. Bajaj, and, R. J. Tayade, Enhanced photocatalytic activity of bismuth-doped TiO₂ nanotubes under direct sunlight irradiation for degradation of Rhodamine B dye. *J. of Nanoparticle Res.*, 15 (2013) 1669. doi.org/10.1007/s11051-013-1669-3